Content available at: <https://www.ipinnovative.com/open-access-journals>

IP International Journal of Medical Microbiology and Tropical Diseases

Journal homepage: <https://www.ipinnovative.com/journals/IJMMTD>

Original Research Article

Chitosan nanoparticles biosynthesis and characterization for Inhalation as an operative treatment of tuberculosis

Emad Rizkallah Zaki¹, Dalia M Mohsen², Dalia Kamal Eldein^{2,*}, Mohamed B. Yousef², Mohammed H Fagir²¹National Research Centre, AHRI, NRC, Egypt²Dept. of Clinical Laboratory Sciences, Inaya Medical Colleges, Saudi Arabia

ARTICLE INFO

Article history:

Received 27-09-2020

Accepted 14-12-2020

Available online 02-01-2021

Keywords:

Biosynthesis of chitosan nanoparticle
Mycobacterium Tuberculosis
pulmonary drug

ABSTRACT

Chitosan nanoparticles have expanded growing attention for Nano-medicine, development of new therapeutic and biomedical engineering with improved availability, increased specificity, and compact toxicity. The present study aim to synthesis and characterize inhalation of chitosan nanoparticles for anti-mycobacterial supply to the lungs. The ionic gelation method followed spray drying was used for chitosan nanoparticles development. The results showed that the obtained particles had a spherical smooth shape with an average size of 255 ± 3.5 nm. Post nebulization drugs were detected in numerous organs (lungs, spleen and liver) till twenty four hours. A single dose of drug-loaded had a chemotherapeutic efficacy more effective against the mycobacterium than other available drugs.

© This is an open access article distributed under the terms of the Creative Commons Attribution License (<https://creativecommons.org/licenses/by/4.0/>) which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

1. Introduction

Mycobacterium Tuberculosis is a communicable disease containing the tubercle bacilli.¹ *Mycobacterium Tuberculosis* is spreads by inhalation airborne droplets containing- bacilli.² The *Mycobacterium tuberculosis* were reported in 95 % of cases in developed countries and million new cases of infection detected each year which is responsible for over two million deaths every year. *Mycobacterium tuberculosis* global incidence rate is highly growing each year by almost 1%. Anti-Tuberculosis drugs resistance continued to be documented as a clinical problem.³ Patient non-compliance to anti-tubercular drug therapy leads to a great therapeutic failure,⁴ In medicines the use of natural products is well known in many developing countries. The natural products privilege that is cheaper, more effective and impart least side effects as compared to synthetic medicines.^{5,6} Thus, increasing examination has been given to chitosan and its derivatives.

Chitosan is derived from naturally occurring sources, including the exoskeletons of arthropods such as shellfish like shrimp, Chitosan contain highly reactive functional groups, high adsorption capacity, Antimicrobial, and anti-fungal, even anti-tumor influence.^{7,8} Chitosan is widely predictable for its effective broad spectrum antimicrobial activity and low toxicity to mammalian cells. Chitosan antimicrobial action mode is not completely understood, the chitosan molecular structure is requirement for its anti- bacterial activity. It is well^{9,10} Chitosan used as an anti-bacterial against a wide range of bacteria, yeasts, and fungi in vivo and in vitro.¹¹ Chitosan antibacterial activity is subjective by a number of factors that include the degree of polymerization and chemical properties.¹²

In new centuries, nanoparticle developments are being widely considered for direct delivery to the lungs via the pulmonary route.¹³ Various biodegradable natural origin polymers (cellulose, gelatin and starch) are used as transporters for drugs, but chitosan was considered for this study due to its biodegradable nature as a non-toxic polymer which has adhesive and membrane permeability. Chitosan

* Corresponding author.

E-mail address: dr.dalia@inaya.edu.sa (D. Kamal Eldein).

can controls the drug release, extending the duration of treatment effects and delivering the drug to the specific sites in body. The pulmonary route escapes the problems by ingestion route such as reduced solubility, thereby lead to reduction in the dosing frequency, and development of patient passivity. The aim of the study is to a bio-synthesis of the chitosan nanoparticles containing rifampicin for antibacterial use. Chitosan nanoparticles have potential role as polymeric platforms for the development of new therapeutic drug release technique with better distribution and increased sensitivity and decrease toxicity against *Mycobacterium Tuberculosis*.

2. Materials and Methods

2.1. Ethical considerations

The research protocols for animal injection is approved by National Research Center (NRC – Animal House system – Biosafety level 3) (Dokki – Egypt). Rifampicin was saved by NRC.

2.2. Biosynthesis of chitosan

Production of chitosan from crustacean shell generally consists of three basic steps: demineralization, deproteinization, and deacetylation.¹⁴ The shells were demineralized by agitating continuously with 5% HCl at the ratio of 1:15 (w/v, shell to solution) 36 h at room temperature. The demineralized shells were treated with 5% NaOH solution at the ratio of shell to solution of 1:10 (w/v) at 90–95°C for 6h. The deproteinized shells were filtered and washed with tap water until NaOH was removed completely, then dried overnight in an oven at 55–60°C. The shells were filtered and washed with tap water until became neutral. Then deacetylation of chitosan was carried out by hydrolyzing with 80% Na OH at the ratio of 1:20 (w/v, chitin to solvent) at 90–95°C for 5 h. This product was washed with tap water until it became neutral and dried overnight at 55– 60°C. In the preparation of chitosan solutions, 1.0% (w/v) chitosans were dispersed in a 1.0% (v/v) acetic acid solution.

Mycobacterium tuberculosis strains H37Rv were obtained from the *Mycobacterium tuberculosis* unit reference strain. Cultured at 37°C in Middlebrook 7H9 broth (Becton Dickinson, Sparks, MD) supplemented with 0.2% glycerol (Sigma Chemical Co., St. Louis, MO) and 10% OADC (oleic acidalbumin-dextrose-catalase; Becton Dickinson) until logarithmic growth was reached. Each culture was mixed with a sufficient volume of sterile supplemented Middlebrook 7H9 broth to achieve a turbidity equivalent to that of McFarland's No. 1 standard. To obtain the test inoculum, this suspension was further diluted 1:50 with the same culture medium to approximately 6×10^6 colony-forming units (CFU)/mL immediately before use. A change in color from blue to pink indicated the

growth of bacteria, and the MIC was defined as the lowest concentration of drug that prevented this change in color.

3. Experimental animals

3.1. Housing conditions

Animal care and all experimental procedures were carried out in accordance with international guidelines governing animal care and use for research. For Female mice (6–8 of weeks age, 20–25 g) were obtained from a nearby provider and the animals are gathered in isolated cages, in controlled temperature (23–25°C), humidity (60%), light and dark cycles of 12 hours each. The animals were encouraged on standard pelleted eat less and water. Mice were kept for at least 3 days earlier to test methods and were ordinarily housed all through the observational period. The mice were particular pathogen free.

3.2. Development and characterization of chitosan Nano-particles drug-loaded

Using gelation technique.¹⁵ Tri-polyphosphate and chitosan solutions were added to each other's (0.5% w/v) containing Rifampicin different amounts, under magnetic stirring. To prepare inhalable nanoparticles, the drug-loaded chitosan Nano-particles were spray-dried with mannitol (1% w/v) and leucine (0.25% w/v), using a dryer. Removal of the powder from the collector vessel and characterization occurred¹⁶ Size characterization of chitosan Nano-particles using polydispersity index on a particle size analyzer (Beckman Coulter Pvt. Ltd., Delsa Nano C). (SEM) Scanning electron microscopy was working for visualization of the optimized nanoparticle shape, The particle size and morphology of synthesized nano particles were determined using a field emission scanning electron microscope (FE-SEM, 15 kV, model 54160, Hitachi, Japan). (Figure1). The amount of anti-tubercular drugs untrapped in the chitosan Nano-particles was calculated by estimating the amount of drug recovered in the supernatant after centrifugation. Dialysis method was used to determine the released drug from chitosan Nano-particles. Samples were withdrawn and analyzed using spectrophotometer (UV-1601 Shimadzu, Japan) Rifampicin content, at 260 nm and 478 nm respectively.¹⁷

3.3. In vivo experimental infection using drug disposition method

In vivo Experimental infection were in animal house level 3 Biosafety and Biosecurity system ,Female mice (6–8 of week age, 20–25 g) were infected with 4×10^7 bacilli/ml in 0.1 ml of 0.9% NaCl, through the aerosol route (inhalation exposure system). The animals were then divided into the following groups: Group 1, control group; Group 2, naïve group; Group 3, free drug, aerosol; and Group 4,

nanoparticle-loaded anti – tuberculosis drugs. The animals were sacrificed after 2 and 4 weeks of the test experiment starts ; lungs was removed, homogenized in sterile normal saline solution and plated Agar plates for (CFU) colony-forming unit estimation on the 14th and 28th days post inoculation.¹⁸ Nebulizer system (Pan Century, USA) was used in this study. Drug disposition studies for single dose, female mice were grouped as follows, with eighty animals in each group: Group 1, free drug, aerosol; and Group 2, nanoparticle-loaded with aerosol anti-tuberculosis drugs. Animals were sacrificed and drug levels were determined in lungs.¹⁹

Fig. 1: SEM images of chitosan nanoparticles size distribution

Minimum Bactericidal Concentration determination by using the paper disc method Chitosan nanoparticles screening and its solvents for antibacterial activity against *Mycobacterium tuberculosis* strain H37Rv were done using the paper disc method.²⁰ For the treatment, each of 0; 150; 300; 600; 1200 $\mu\text{g/mL}$ chitosan nanoparticles solutions were slowly absorbed into the sterilized paper disc (diameter: 8 mm) and adhered to the surface of the plate on which *Mycobacterium tuberculosis* strains H37Rv at a concentration of 106 CFU/ml had been inoculated in Middlebrook 7H9 broth. Sterilized distilled water was used as a control. After culturing for 24 h in an incubator at 37°C. Antibacterial activity was defined as the diameter (mm) of the clear inhibitory zone formed around the discs. MBC was defined as the lowest concentration that induced the clear inhibitory zone formed around the discs.

3.4. Statistical analysis

Statistical tests were performed with Graph-Pad Soft- ware. A difference with a value of $p < 0.05$ was considered statistically significant.

4. Results and Discussions

Tuberculosis is a chronic disease caused by *Mycobacterium tuberculosis*. The emergence of antibiotic-resistant strains of this species underscores the need for new effective drugs against resistant mycobacteria as medications.²¹ The uses of natural product as traditional medicines are accepted, particularly in developing countries. This led us to the investigation of the effects of chitosan nanoparticles from shrimp on anti-mycobacterial activity.

Chitosan nanoparticles had a spherical shape with an average size of 230 - 4.5 nm. (Figure 1). We modified chitosan into chitosan nanoparticles with used sodium

Tri-polyphosphate to prepare chitosan nanoparticles by inotropic gelation method, which has more advantages over chitosan. Due to this modification can improve bio-distribution and increase specificity and sensitivity, and reduced pharmacological toxicity.¹⁹ The topography, surfaces, structures, morphologies, and composition of the chitosan nanoparticles were studied using Scanning Electron Microscopic.¹⁸ The Scanning Electron Microscopic micrograph obtained for the pure chitosan revealed that the texture is plain without pores having smooth, compact and homogeneous even surface structure with no gross effects. While the SEM micrograph of chitosan nanoparticles revealed the rough surface morphology. The Scanning Electron Microscopic picture of chitosan nanoparticles demonstrates the good dispersion of the nanoparticles which are entangled one on the other with a larger exposed surface making the material very suitable for adsorption.

Nanoparticles are easily captured by the alveolar macrophage of lungs.¹⁸ The higher drug encapsulation observed for Chitosan nanoparticles in this study can be attributed to the higher drug/polymer ratio, as well as an excellent ionic gelation between Tri-polyphosphate and chitosan.²² The release behavior of Rifampicin from the Nano particulate formulation followed a biphasic pattern, that is, an initial burst (40–50% within 5 hours) followed by a slower sustained release (90–95% for up to 72 hours) . An initial burst release of RIF from nanoparticles could be due to rapid dissolution of drug crystals located on the surface or present beneath the nanoparticle surface.¹⁴

4.1. The effect of chitosan nanoparticles against *Mycobacterium tuberculosis* on the paper method

Chitosan nanoparticles anti-mycobacterial activity was done using the paper disc method. MIC was defined as the lowest concentration that induced the clear inhibitory zone formed around the discs. The MIC of chitosan nanoparticles against *Mycobacterium tuberculosis* strains H37Rv was 1200 $\mu\text{g/mL}$, which induced the clear inhibitory zone formed around the disc. The MIC of the chitosan nanoparticles against *Mycobacterium tuberculosis* was conducted on the paper disc method. In this study, MIC of chitosan nanoparticles against *Mycobacterium tuberculosis* strains H37Rv was 1200 $\mu\text{g/mL}$. These results are in agreement with reports in the literature that have documented the antibacterial activity of chitosan against a large number of both gram positive and negative bacteria. Some researcher has also shown that chitosan generally showed stronger effects for gram positive bacteria (e.g. *Staphylococcus aureus*) and for gram negative bacteria (e.g. *E. coli*).

Fig. 2: Treatment efficacy 1- control group, 2-Rifampicin treated group and 3- anti-tuberculosis chitosan treated.

4.2. In vivo drug disposition studies

Chitosan nanoparticles were administered through nebulization, the superiority of the anti- tuberculosis drugs loaded Chitosan nanoparticles was seen in comparison to the anti- tuberculosis drugs plain drug in increasing the accumulation of within the organs rich in macrophages, that is, lungs. Both drugs were detected in lungs, for up to 24 hours, thus prompting us to design the nebulized drug-loaded Chitosan nanoparticles for treatment. The higher lung uptake of Chitosan nanoparticles may be attributed to preferential phagocytosis by macrophages and localization in alveolar macrophages.⁹

4.3. Chemotherapeutic efficacy

Administration of nebulized Chitosan nanoparticles for 28 days to infected mice resulted in undetectable mycobacterial CFUs in lung (Table 1). Observations suggested that Chitosan nanoparticles are more effective against the

mycobacterium than free drugs (Figure 2). The efficacy of chitosan nanoparticle formulations shows an effective targeting to macrophage-rich organs in treating the disease.²⁰

Table 1: Chemotherapeutic efficacy of various formulations (mean $\pm$ S.D., n=6)

Log ₁₀ CFU Lungs	Groups
1.15	Untreated control
1.34	Free Rifampicin
0.19	Anti- tuberculosis drugs loaded chitosan nanoparticles

5. Conclusions

The results from this research can be concluded that chitosan nanoparticles have anti-tubercular activity by In vitro techniques. Therefore, it has the definite potential as a source of compounds that may be developed further into anti-mycobacterial drugs. Furthermore rug-loaded Chitosan nanoparticles were successfully synthesized and characterized as an effective delivery carrier for alveolar macrophage targeting. Finally, it may be concluded that Chitosan nanoparticles may be exploited as a prospective tool for drug delivery to direct drugs to the lung tissues for the treatment of TB.

6. Source of Funding

No financial support was received for the work within this manuscript.

7. Conflict of Interest

The authors declare they have no conflict of interest.

References

1. Chaubey P, Mishra B. Mannose-conjugated chitosan nanoparticles loaded with rifampicin for the treatment of visceral leishmaniasis. *Carbohydrate Polym.* 2014;101:1101–8. doi:10.1016/j.carbpol.2013.10.044.
2. Patel S, Chavhan S, Soni H, Babbar AK, Mathur R, Mishra AK, et al. Brain targeting of risperidone-loaded solid lipid nanoparticles by intranasal route. *J Drug Target.* 2019;19(6):468–74.
3. Sospeter NN, Meshack AO, Silas MN, Samwel NO, John MN, Paul KK, et al. Antituberculous, antimicrobial, cytotoxicity and phytochemical activity study of *Piliostigma thonningii* extract fractions. *J Med Plants Res.* 2015;9(22):655–63. doi:10.5897/jmpr2015.5822.
4. Pabreja S, Garg T, Rath G, Goyal AK. Mucosal vaccination against tuberculosis using Ag85A-loaded immunostimulating complexes. *Artif Cells, Nanomedicine, Biotechnol.* 2016;44(2):532–9. doi:10.3109/21691401.2014.966195.
5. Sudjarwo SA, Eraiko K, Wardani G, Koerniasari. The potency of chicken egg yolk immunoglobulin (IgY) specific as immunotherapy to *Mycobacterium tuberculosis* infection. *J Adv Pharm Technol Res.* 2017;8(3):91–6.
6. Fadipe VO, Mongalo NI, Opoku AR, Dikhoba PM, Makhafola TJ. Isolation of anti-mycobacterial compounds from *Curtisia dentata*

- (Burm.f.) C.A.Sm (Curtisiaceae). *Bio Med Central Complement Altern Med*. 2017;17(1):306–13. doi:10.1186/s12906-017-1818-9.
7. Kong M, Chen XG, Xing K, Park HJ. Antimicrobial properties of chitosan and mode of action: A state of the art review. *Int J Food Microbiol*. 2010;144(1):51–63. doi:10.1016/j.ijfoodmicro.2010.09.012.
 8. Goy RC, de Britto D, Assis OBG. A review of the antimicrobial activity of chitosan. *Polímeros*. 2009;19(3):241–7. doi:10.1590/s0104-14282009000300013.
 9. Ngamviriyavong P, Thananuson A, Pankongadisak P, Tanjak P, Janvikul W. Antibacterial hydrogels from chitosan derivatives. *J Met Mater Miner*. 2018;20(3):113–7.
 10. Kaya M, Baran T, Asan-Ozusaglam M. Extraction and characterization of chitin and chitosan with antimicrobial and antioxidant activities from cosmopolitan Orthoptera species. *Biotechnol Bioprocess Eng*. 2019;20(1):168–79.
 11. Friedman M, Juneja VK. Review of antimicrobial and antioxidative activities of chitosans in food. *J Food Prot*. 1737;73(9):1737–61.
 12. Wardani G, Mahmiah, Sudjarwo SA. A Multifaceted Journal in the field of Natural Products and Pharmacognosy. 2018;10(1):162–6.
 13. Garg T. Current nanotechnological approaches for an effective delivery of bio-active drug molecules in the treatment of acne. *Artif Cells Nanomed Biotechnol*. 2016;44(1):98–105.
 14. Younes I, Rinaudo M. Chitin and Chitosan Preparation from Marine Sources. Structure, Properties and Applications. *Marine Drugs*. 2015;13(3):1133–74. doi:10.3390/md13031133.
 15. Kaur R, Garg T, Gupta UD, Gupta P, Rath G, Goyal AK, et al. Preparation and characterization of spray-dried inhalable powders containing nanoaggregates for pulmonary delivery of anti-tubercular drugs. *Artif Cells Nanomed Biotechnol*. 2016;44(1):1–6. doi:10.3109/21691401.2014.930747.
 16. Kaur R, Garg T, Malik B, Gupta UD, Gupta P, Rath G, et al. Development and characterization of spray-dried porous nanoaggregates for pulmonary delivery of anti-tubercular drugs. *Drug Deliv*. 2016;44(6):1498–507. doi:10.3109/10717544.2014.920428.
 17. Sharma A, Garg T, Aman A, Panchal K, Sharma R, Kumar S, et al. Nanogel—an advanced drug delivery tool: Current and future. *Artif Cells Nanomed Biotechnol*. 2016;44(1):165–77. doi:10.3109/21691401.2014.930745.
 18. Marwah H, Garg T, Goyal AK, Rath G. Permeation enhancer strategies in transdermal drug delivery. *Drug Deliv*. 2016;23(2):564–78. doi:10.3109/10717544.2014.935532.
 19. Pabreja S, Garg T, Rath G, Goyal AK. Mucosal vaccination against tuberculosis using Ag85A-loaded immunostimulating complexes. *Artif Cells Nanomed Biotechnol*. 2016;44(2):532–9.
 20. Nyambuya T, Mautsa R, Mukanganyama S. Alkaloid extracts from *Combretum zeyheri* inhibit the growth of *Mycobacterium smegmatis*. *BMC Complement Altern Med*. 2017;17(1):124–30. doi:10.1186/s12906-017-1636-0.
 21. World Health Organization. Global Tuberculosis Report 2015. 20 Avenue Appia, 1211 Geneva 27, Switzerland: World Health Organization; 2015.
 22. Hussain T, Garg T, Goyal AK, Rath G. Biomedical Applications of Nanofiber Scaffolds in Tissue Engineering. *J Biomat Tissue Eng*. 2014;4(8):600–23. doi:10.1166/jbt.2014.1214.

Cite this article: Zaki ER, Mohsen DM, Kamal Eldein D, Yousef MB, Fagir MH. Chitosan nanoparticles biosynthesis and characterization for Inhalation as an operative treatment of tuberculosis. *IP Int J Med Microbiol Trop Dis* 2020;6(4):198-202.